

2. (Original) The electronically tunable dielectric material of Claim 1, wherein the additional metal oxide phases comprise a total of from about 3 to about 65 weight percent of the material.

3. (Original) The electronically tunable dielectric material of Claim 1, wherein the additional metal oxide phases comprise a total of from about 5 to about 60 weight percent of the material.

4. (Original) The electronically tunable dielectric material of Claim 1, wherein the additional metal oxide phases comprise a total of from about 10 to about 50 weight percent of the material.

5. (Original) The electronically tunable dielectric material of Claim 1, wherein the dielectric material consists essentially of two of the additional metal oxide phases.

6. (Original) The electronically tunable dielectric material of Claim 5, wherein the two additional metal oxide phases have a weight ratio of from about 1:100 to about 100:1.

7. (Original) The electronically tunable dielectric material of Claim 5, wherein the two additional metal oxide phases have a weight ratio of from about 1:10 to about 10:1.

8. (Original) The electronically tunable dielectric material of Claim 5, wherein the two additional metal oxide phases have a weight ratio of from about 1:5 to about 5:1.

9. Cancel claim 9.

10. Cancel claim 10

11. (Currently amended) The electronically tunable dielectric material of Claim 1[0], wherein the barium strontium titanate is of the formula $Ba_xSr_{1-x}TiO_3$, where x is from about 0.15 to about 0.6.

12. Cancel claim 12.

13. Cancel claim 13.

14. Cancel claim 14.

15. (Currently Amended) The electronically tunable dielectric material of Claim 1[4], further comprising at least one Mg-free compound.

16. (Original) The electronically tunable dielectric material of Claim 15, wherein the Mg-free compound comprises an oxide of a metal selected from Si, Ca, Zr, Ti and Al.

17. (Original) The electronically tunable dielectric material of Claim 15, wherein the Mg-free compound comprises a rare earth oxide.

18. Cancel claim 18.
19. Cancel Claim 19.
20. Cancel Claim 20.
21. Cancel Claim 21.
22. (Original) The electronically tunable dielectric material of Claim 1, wherein the material has a tunability of at least 25 percent at 8V/micron.
23. (Original) The electronically tunable dielectric material of Claim 1, wherein the material has a tunability of at least 30 percent at 8V/micron.